

# Temperature Dependence of Material Properties and its Influence on the Thermal Distribution in Regeneratively Cooled Combustion Chamber Walls

#### M. Oschwald, D. Suslov, A. Woschnak

German Aerospace Center Institute for Space Propulsion, Lampoldshausen D-74239 Hardthausen

1st EUCASS July 4-7, 2005 Moscow, Russia



# conditions in regeneratively cooled LOX/GH<sub>2</sub>-engines

- ▶ hot gas temperature: ≈ 3500 K
- ▶ pressure: ≈ 11 MPa
- heat flux: up to 80 MW/m<sup>2</sup>
- LH<sub>2</sub>-temperature:
  - cooling channel inlet  $\approx 40 \text{ K}$
  - cooling channel outlet  $\approx 100 \text{ K}$
- wall structure temperature:
  - hot gas side  $\approx 400 800 \text{ K}$
  - cooling fluid side  $\approx 40 100 \text{ K}$

#### hot gas wall temperature: $\Delta T$ =40 K $\approx$ 50% life time

A. Fröhlich, M. Popp, G. Schmidt, D. Thelemann. Heat Transfer Characteristics of  $H_2/O_2$ Combustion Chambers, AIAA 93-1826, 29th Joint Propulsion Conference, Monterey, CA, 1993





# stratification in cooling channels with high aspect ratio

#### HARCC-experiment

- P8 test bench
- LH<sub>2</sub>-cooled L42 combustor
- pressures up to P<sub>c</sub> = 9 MPa
- heat fluxes up to 40 MW/m<sup>2</sup>
- variation of AR=1.7 ... 30



#### P8 test bench —

D. Suslov, A. Woschnak, J. Sender, M. Oschwald, Test specimen design and measurement technique for investigation of heat transfer processes in cooling channels of rocket engines under real thermal conditions, AIAA 2003-4613, 39th Joint Propulsion Conference, Huntsville, 2003

A. Woschnak, D. Suslov, M. Oschwald, Experimental and Numerical Investigations of Thermal Stratification Effects, AIAA 2003-4615, 39th Joint Propulsion Conference. Huntsville, 2003





# **HARCC** geometries

sector no.	width [mm]	height [mm]	aspect ratio	fin width [mm]
1	1.2	2.0	1.7	1.4
2	0.8	2.8	3.5	1.4
3	0.3	9.0	30	1.4
4	0.5	4.6	9.2	1.4







# temperature determination in wall structure with thermocouples

- measurements at 4 axial locations
  - z=52mm, 85mm, 119mm, 152mm downstream duct entrance
- 5 radial positions
  - 0.7mm, 1.1mm, 1.5mm, 1.9mm, 7.5mm from hot gas side
- determination of surface temperature, heat flux and heat transfer coefficients by inverse method







### heat conduction / material properties

#### instationary problem:

$$\rho \frac{\partial (c_V T)}{\partial t} - \nabla \cdot (\lambda \nabla T) = 0$$

stationary problem:

$$-\nabla \cdot (\lambda \nabla T) = 0$$

specific heat:

heat conductivity:

 $c_V \approx 25.9 \text{ J/mol/K}$ (Dulong-Petit, ambient temperature)  $\lambda \approx 350 \text{ W/Km}$ (typical Cu-alloy)



combustion chamber wall construction



## **Debye-theory of the specific heat**



**Debey-theory** 

- quantum mechanics for low temperature behaviour
- high temperature limit:

c<sub>v</sub> = 3R (Dulong-Petit)

Iow temperature limit:

 $\textbf{c}_V \propto a {\cdot} (\textbf{T} / ~ \boldsymbol{\Theta}_D ~ \textbf{)^3}$ 

• for copper:  $\Theta_{\rm D} \approx 315$  K



### thermal conductivity at low temperatures



R.L. Powell and W. A. Blanpied, Thermal Conductivity of Metals and Alloys at Low Temperature, NBS Circular 556, 1954 Institute of Space Propulsion



# thermal conductivity of copper alloy for L42-combustor





### thermal expansion coefficient





# thermal field w/o and with temperature dependence of $\lambda$

 HARCC experiment, 52 mm downstream cooling fluid inlet

AR H/B	sector	Т <sub>Н2</sub>	<i>Т<sub>W</sub></i> [К]		∆T <sub>W</sub> [K]
			$T_c$ $\lambda$ =const.	τ <sub>ν</sub> λ(Τ)	
1.7	Q1	85	380.9	385.0	4.9
3.5	Q2	90	363.3	369.4	6.1
9.1	Q4	95	349.9	358.2	8.3
30	Q3	100	343.6	352.7	9.1







# thermal field w/o and with temperature dependence of $\lambda$

cooling fluid temperature: 50K

AR H/B	sector	<i>Т<sub>W</sub></i> [К]		⊿T <sub>w</sub> [K]
		$T_c$ $\lambda$ =const.	τ <sub>ν</sub> λ(τ)	
1.7	Q1	349.0	361.3	12.3
3.5	Q2	326.6	345.7	19.1
9.1	Q4	308.3	334.6	26.3
30	Q3	297.3	327.0	29.7

 $\Delta T_W = T_v - T_c$ 





# transient thermal field: $c_v = c_0 vs. c_v = c_v (T)$

#### wall temperatures

- pre-cooling of structure to 40 K
- instantaneous temperature increase at t=0

C •

b

а





# transient thermal field: $c_v = c_0 vs. c_v = c_v (T)$

dT/dt [K/s]

#### temporal gradients







# transient thermal field: $c_v = c_0 vs. c_v = c_v (T)$

#### spatial gradients







#### summary

specific heat  $c_v$ thermal conductivity  $\lambda$ thermal expansion coefficient  $\alpha$ 

- show significant temperature dependence
- $c_v$ ,  $\lambda$ ,  $\alpha$  disappear at absolute zero

 $\alpha \rightarrow 0 \text{ for } T \rightarrow 0$ 

• reduced thermal stress at low temperature

 $c_v \rightarrow 0$  für T $\rightarrow 0$ 

• only minor differences as compared with simulation results with c<sub>v</sub>=const.

 $\lambda \rightarrow 0 \text{ for } T \rightarrow 0$ 

- increase of hot gas side wall temperature
- relevant level of increase at low cooling fluid temperature and high AR